

Standard fitting:

Normal ductile (A) reinforcing steel B500A
 Yield strength $R_e^{1)} \geq 500 \text{ MPa (N/mm}^2\text{)}$
 Ratio of tensile strength / yield stress $R_m / R_e^{1)} \geq 1.05$
 Elongation at tensile strength $A_{gt} \geq 2.5\%$
¹⁾ or 0.2% proof strength respectively


Diagonals smooth surface (B500A+G),
 Upper chord and lower chords ribbed (B500A)

Unusual quality:

Other steel qualities, surfaces and distances between welding points are possible on request.

Production mark:

(on the ribbed bars)






Pattern of description:

SWE 22 - 06 5 06
 Girder height: 220 mm
 Diameter of lower chord: 6 mm
 Diameter of diagonals: 5 mm
 Diameter of upper chord: 6 mm

Delivery length:

Multiple distance between welding points

Country	Technical approval / Standard	Certificate
Germany	German Institute for Building Technology DIBt Z-15.2-40 (semi-precast wall)	Civil Engineering Materials Testing Institute MPA Braunschweig Zert-1/429-p/10 
Norway	German technical approval	Kontrollradet 961226 
Sweden		SBS Nordcert 

Some certificates cover special lattice girder dimensions, deviant material properties and are valid only for particular production plant